IN THE CLAIMS:

- (Previously Presented) A method of kinetic spray coating a substrate comprising the steps of:
 - a) providing particles of a powder;
- b) injecting the particles into a gas/powder exchange chamber and entraining the particles into a flow of a main gas in the gas/powder exchange chamber, the main gas at a temperature insufficient to heat the particles to a temperature above a melting temperature of the particles:
- c) directing the particles entrained in the main gas from the gas/powder exchange chamber into a powder/gas conditioning chamber downstream from the gas/powder exchange chamber; and
- d) directing the particles entrained in the flow of the main gas from the powder/gas conditioning chamber into a converging diverging supersonic nozzle, thereby accelerating the particles to a velocity sufficient to result in adherence of the particles on the substrate positioned opposite the nozzle, the powder/gas conditioning chamber having a length along a longitudinal axis of equal to or greater than 80 millimeters to provide a residence time that the particles are exposed to the main gas between the gas/powder exchange chamber and the nozzle that is sufficient to increase a temperature of the particles between the gas/powder exchange chamber and the nozzle and facilitate adherence of the particles to the substrate without heating the particles to a temperature above the melting temperature of the particles.
- (Original) The method as recited in claim 1, wherein step a) comprises
 providing as the particles at least one of an alloy, a metal, a ceramic, a polymer, a metal
 coated ceramic, a semiconductor, or mixtures thereof.

- (Original) The method as recited in claim 1, wherein step a) comprises providing particles having an average nominal diameter of from about 1 microns to 250 microns
- (Original) The method as recited in claim 1, wherein step b) comprises
 injecting the particles under a pressure that is from about 5 to 300 pounds per square inch
 above a pressure of the main gas.
- (Original) The method as recited in claim 1, wherein the main gas is at a temperature of from about 200 to 1000 degrees Celsius
- (Original) The method as recited in claim 1, wherein step b) comprises injecting the particles parallel to a longitudinal axis of the gas/powder exchange chamber.
- 7. (Original) The method as recited in claim 1, wherein step b) comprises injecting the particles at one of an oblique angle relative to a longitudinal axis of the gas/powder exchange chamber or at a tangential angle relative to the gas/powder exchange chamber.
- (Previously Presented) The method as recited in claim 1, wherein the length
 of the powder/gas conditioning chamber is from about 80 millimeters to about 1000
 millimeters.
- (Original) The method as recited in claim 1, wherein step d) comprises accelerating the particles to a velocity of from about 200 to about 1500 meters per second.

10. (Original) The method as recited in claim 1, wherein step d) comprises providing a substrate comprising at least one of a metal, an alloy, a plastic, a polymer, a ceramic, a wood, a semiconductor or a mixture thereof.

11-20. (Canceled)

- 21. (Previously Presented) The method as recited in claim 1, wherein the temperature of the particles increases from about 150 degrees Kelvin to about 250 degrees Kelvin as the particles travel in the powder/gas conditioning chamber from the gas/powder exchange chamber to the nozzle.
- 22. (Previously Presented) The method as recited in claim 1, wherein step b) comprises directing the main gas through a flow straightener, the powder/gas conditioning chamber being disposed downstream of the flow straightener and upstream of the nozzle.

(Canceled)

24. (New) The method as recited in claim 1, wherein the gas/powder exchange chamber is defined within a first housing portion and the powder/gas conditioning chamber is defined within a second housing portion disposed between the first housing portion and the nozzle, the second housing portion releasably engaging both the first housing portion and the nozzle.